



2015001701W

Cert. No: LF20160463



中国认可
国际互认
检测
TESTING
CNAS L0269

Certificate of Test

Client: Yongkang Longkui Protective Equipment Co., Ltd

Address: No.366, Kechuang Road, the Economic Development Zone,
Yongkang City, Zhejiang Province

Sample Name: Ballistic Helmet

Physical and Chemical Inspection Center in Non-metals
Material of Ordnance Industries

Nov.14.2016

NOTES

1. Without business seal and paging seal the certificate is invalid.
2. Without approver signature the certificate is invalid.
3. Without the written approval of our laboratory, the certificate should not be reproduced except in full.
4. This Certificate is based on data obtained from having test only the samples submitted and should not be interpreted as an endorsement by Physical and Chemical Inspection Center in Non-metals Material of Ordnance Industries of the continuing quality, or performance, of any other items of the same, or similar design.
5. All instrumentation and measurement devices were calibrated in accordance with ISO 17025 Requirements.

Add.: No.3 Tianjiazhuang east road, Tianqiao District, Jinan

P.O. Box 108, Jinan, China

Zip: 250031

Tel.: +86-0531-85878142

Fax: +86-0531-85878162

Physical and Chemical Inspection Center
in Non-metals Material of Ordnance Industries
Certificate of Test

Page 2 of 5

Cert. №: LF20160463

Sample Name	Ballistic Helmet	Test Type	Consignation Test
Client	Yongkang Longkui Protective Equipment Co., Ltd	Address	No.366, Kechuang Road, the Economic Development Zone, Yongkang City, Zhejiang Province
Contact Person	Jet Shi	Phone	18969388688
Date Received	11/10/2016	Date Tested	11/10/2016
Sample Amount	1	Sample No.	LK-FDK-04
Categories	Ballistic Resistance	Test Standard	NIJ 0106.01 & NIJ 0108.01 IIIA (.44 Magnum SJHP)

The Ballistic helmet (Sample No.: LK-FDK-04) provided by Yongkang Longkui Protective Equipment Co., Ltd was tested according with NIJ 0106.01 & NIJ 0108.01 IIIA (.44 Magnum SJHP). The test results show that no perforation occurs after five fair shots at different points of the sample with .44 Magnum SJHP under normal temperature and humidity. The maximum of the Backface Signature(BFS) depth is 31.2mm.

Laboratory configuration, sample description and test results are showed from Page 3 to 5.

Test Conclusion

Physical and Chemical Inspection Center
in Non-metals Material of Ordnance Industries

Nov.14.2016

Prepared By: Wang Wei

Reviewed By: Peng Gang

Approved By: Feng Guohao

Physical and Chemical Inspection Center
in Non-metals Material of Ordnance Industries
Certificate of Test

Page 3 of 5

Cert. №: LF20160463

Laboratory Configuration	
Test Unit	Physical and Chemical Inspection Center in Non-metals Material of Ordnance Industries
Ambient Test Conditions	Temperature: 17°C; Relative Humidity: 55%.
Setup	Weapons: Ballistic Barrel Bullets: .44 Magnum SJHP Electrical chronometer. Standard measures. Electronic Balance.
Test Range	5m
Angle of Incidence	0°
Sample Description	
Sample No.	LK-FDK-04
Configuration	PE composites
Remarks	Blank
Recorded By: Wang Wei	Checked By: Wang Ruoyi

Physical and Chemical Inspection Center
in Non-metals Material of Ordnance Industries
Certificate of Test

Page 4 of 5

Cert. №: LF20160463

Results of Ballistic Resistance Test


Sample Parameters				
Sample No.	Thickness(mm)	Weight (g)	Conditioning	
LK-FDK-04	8.7	896	Normal Temperature and Humidity	
Test Results				
Shot No.	Impact Point	Velocity(m/s)	Results	BFS Depth(mm)
1	Front	428.6	Stop	31.2
2	Back	430.8	Stop	27.7
3	Left	429.7	Stop	23.5
4	Right	438.5	Stop	20.8
5	Top	439.1	Stop	28.6
	Blank			
Tested By: Wang Wei		Checked By: Wang Jueai		

Physical and Chemical Inspection Center
in Non-metals Material of Ordnance Industries
Certificate of Test


Page 5 of 5

Cert. №: LF20160463


Attached Pictures



(a) front



(b) back



(c) left



(d) right



(e) top



(f) inside

Fig. 1 Ballistic Helmet LK-FDK-04 (after testing)